

**AMENDMENTS TO THE SPECIFICATION**

**Please replace Table 2, on page 23 with the following amended Table 2:**

Table 2

Various physical properties of barium titanate powder

	Loose bulk density	packed bulk density	Atomic ratio Ba/Ti	chlorine content
<del>Example 1</del>	g/cm <sup>3</sup>	g/cm <sup>3</sup>		ppm
Example 2 <del>1</del>	1.61	2.04	1.000	26
Example 3 <del>2</del>	1.55	2.00	1.001	35
Example [[4]] <del>3</del>	1.44	2.00	0.998	46
<del>Comparative Example 4</del>	1.45	1.92	0.997	29
Comparative Example 1	1.40	1.78	0.998	-
Comparative Example 2	1.08	1.45	0.997	57
Comparative Example 3	1.07	1.45	0.997	-